

HB-EPOXY POLYAMINE

NF-133-SF

Curing Agent: NF-133-CA

Description

Nilifam 133-SF is a high-build, modified two-component epoxy paint, which cures to coating with good resistance to water, splashes of mineral oils, aliphatic hydrocarbons, and to abrasion and impact. Limited resistance to aromatic and stronger solvents and to acids and oxidizing materials.

Nilifam 133-SF As a topcoat with no maximum recoating interval in EPOXY/POLYURETHANE systems.

CURING AGENT NF-133-HB-CA, polyamine, is typically for use above 5°C/41°F.

Recommended use

Excellent to both primed & grit blasted and manually prepared steel surfaces (4A).
Excellent on correctly prepared steel surfaces and primed surfaces.

Dry: Maximum 120°C

physical Properties

Colours	Grey /RAL No
Finish	Flat
Solid by Volume-%	95±2
Theoretical spreading rate	0.95 m ² /lit-1000 Mic 39.9 sq.ft./US gallon-2 mils
Flash point	28°C/83°F
Specific gravity	1.75 kg/lit-16.9 lbs/US gallon
V.O.C.	Max. 60 gr/lit
Shelf life	1 Year (25°C / 77°F) from time of production. Depending on storage condition, mechanical stirring may be necessary before usage.

Application Details

Mixing ratio (by weight)	Component A NF-133-SF 6.67	Component B NF-133-SF-CA 1
Pot life	5 hours (20°C/ 68°F)	

Conditions	Do not apply when relative humidity exceeds 80% or when the surface to be coated is less than 3°C above the dew point.	
Method	Airless sprays	Brush (touch-up)
Thinner (max. vol.)	-	-
Spray setting		
Pump ratio minimum	40:1	
Tip size	0.021"–0.019"	
Tip pressure	150 bar/2100 Psi	
Cleaning of tools	-	
Indicated film thickness, dry	950 micron	
Indicated film thickness, wet	1000 micron	

Drying and Curing Times At (20°C)

Dry to touch	4 hours
Hard dry	1 day
Full curing	7 days
Recoat interval, Min	8 hours
Recoat interval, Max	14 days, see REMARKS

Surface Preparation

New steel	Steel surface should ideally be abrasive blast cleaning to minimum Sa 2½. The surface must be completely clean and dry prior to application. And its temperature must be at least 3°C above the dew point to avoid condensation.
Primed surfaces	The surface should be stable, firm, dry and free of dust, sand, loose old paint, dirt, grease and oil. It is recommended to apply mid coat before exceeding maximum interval of primer.

Remarks

Preceding Coat Epoxy primers such as NF-113

Subsequent Coat -

Film thickness May be specified in another film thickness than indicated depending on purpose and area of use.
This will alter spreading rate and may influence drying time and recoating intervals. Normal range is 50-125 microns/ 2-5 mils.

Thinning Don't use thinner.

Recoating and Drying/Curing time Recoating intervals related to later conditions of temperature:
(75 micron/3 mils dry film thickness)

Physical data versus temperatures:					
Surface temperature		5°C/41°F	10°C/50°F	20°C/68°F	30°C/86°F
Dry to touch approx.		16 hours	8 hours	4 hours	3 hours
Resist condensing humidity/ light showers after		4 days	2 days	24 hours	12 hours
Fully cured		20 days	14 days	7 days	5 days
Recoating interval with epoxy and polyurethane top coats	Min	24 hours	16 hours	8 hours	4 hours
	Max	60 days	30 days	14 days	10 days

A completely clean surface is mandatory to ensure intercoat adhesion, especially at long recoating intervals. Any dirt, oil, and grease have to be removed, e.g. with suitable detergent. Salts should be removed by fresh water hosing. To check an adequate quality of the surface cleaning a test patch is recommended before actual recoating.

Safety

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult Nilifam material safety data sheets and follow all local and national safety regulations. Harmful or fatal if swallowed; immediately seek medical assistance. Avoid inhalations of possible solvent vapors or paint mist, as well as paint contact with skin and eyes. Apply only on well-ventilated areas and ensure that adequate forced ventilation exists when applying paint in confined spaces or when the air is stagnant. Always take precautions against the risks of fire and explosions.